

# **Technical** Data Sheet



### Typical Inspection Data: Colour Grey/black Texture Smooth 2 (meduim) **NLGI Worked Penetration** 285 **Drop Point** 185 **Operating Temperature** -10 to 120 °C Range Oil Separation (168 hours @ <6% 40°C) Water Washout @38°C <7% Timken OK load 1350 lbs

## **Turntable Grease**

## NGLI 23

#### **Product Features:**

- Lithium-based grease fortified with graphite
- Specially formulated for the lubrication of the fifth wheel couplings on articulated vehicles
- Highly water resistant, very adhesive for extended service
- Withstands high levels of shock loading

#### Directions for use:

- Never over pack the bearing
- It is sound lubrication practice to remove the old grease before new grease is applied. If used grease cannot be removed, Comma Turntable Grease is generally compatible with other lithium greases. When mixed with other grease types, this grease should be satisfactory below an operating temperature of 80°C

#### Handling:

- Avoid extremes of temperature
- Store under cover
- Product in cardboard cartons must be stored under cover and away from damp conditions
- Barrels should be stored under cover if possible
- If barrels must be stored outside then lay them on their side to prevent water collecting around the bungs

#### Shelf life:

- 5 years from date of manufacture
- Manufacture date can be identified from an eight digit code printed on the bottle. YYYY.MM.DD

**UPDATED:** 13.09.2024